

Glass Crystallization Research — A 36-Year Retrospective. Part I, Fundamental Studies*

Edgar D. Zanotto[†]

Department of Materials Engineering, Vitreous Materials Laboratory – LaMaV, Federal University of São Carlos, 13.565-905, São Carlos, SP Brazil

Over the past 36 years, our research has mainly focused on the crystallization kinetics and properties of glasses and glass-ceramics. A sampling of the most conclusive papers are reviewed here and include the following topics: the effects of liquid phase separation on crystal nucleation; tests and development of models of crystal nucleation, growth, and overall crystallization; metastable phase formation; surface crystallization; glass stability against devitrification; glass-forming ability; possible correlations between the molecular structure and the nucleation mechanism; sintering with concurrent surface crystallization; and diffusional processes that control crystallization. We conclude that despite significant advancement in the knowledge about several aspects of phase transformations in glasses that resulted from our own research and of other groups, which is not described in this review, *glass crystallization* remains an open, rich field to be explored.

Introduction

I begin with apologies because this article is based on my 2012 *G. W. Morey* award talk; therefore, I only summarized and discuss work on glass crystallization processes from our own group and collaborators and, as a result, leave aside several important papers published by other authors. In addition, due to space restrictions, no equations, figures or other details are shown in this review paper; the interested reader is cordially invited to consult the cited references for further details.

The nature and kinetics of crystallization is a vital scientific problem that governs the glass-forming ability (GFA) of molten liquids and the ultimate stability (GS) of glass against devitrification. Over the last 36 years, our research has mainly focused on fundamental studies of glass crystallization. The first step of the crystallization process — nucleation — is essentially a *nanoscale* phenomenon that faces some difficulties, not only on the theoretical side, but also in the choice and application of experimental techniques and interpretation of results. However, such studies are essential for understanding the vitreous state, as we will show in this article, and for the successful development of useful glass-ceramics, which are described in Part II.¹ Our strategy has been to strike a balance between purely fundamental research and some technological development;

*Article based on the *G. W. Morey award* talk delivered at the Glass and Optical Materials Division meeting, ACerS, Saint Louis, MO, USA, May 2012.

[†]dedz@ufscar.br

we always try to maximize the study of previous articles combined with careful planning and simulations, to optimize the experimentation process. In this article, we summarize a relevant part of our scientific studies.

Effects of Liquid–Liquid Phase Separation on Crystal Nucleation

I was introduced to glass research in 1976 by the late O. J. Whittemore (Professor at Washington University, Seattle, WA) then visiting Professor at the Federal University of São Carlos and continued in 1977 during my MSc dissertation work in Physics at the University of São Paulo under the supervision of Aldo Craievich. During this time, I also attended several lectures about glass by the late visiting American Professor Charles Greene (then retired from Alfred University, Alfred, NY).

The same line of investigation continued during my PhD studies at Sheffield University under the guidance of the late Peter James from 1979 to 1982. We continued to work on a particular problem, described below, until 1986. Due to the strong controversy that existed in the international literature at that time, we performed a detailed, systematic study aiming to establish the effects of metastable liquid–liquid phase separation (LLPS) on the kinetics of crystal nucleation and growth in glasses. We used several lithium silicate and barium silicate glasses, both with and without LLPS, and characterized the concurrent development of these two phenomena — LLPS and crystal nucleation — using optical and electron microscopy techniques as well as small angle X-ray scattering (SAXS).^{2–6}

To give an example of such work,⁶ we studied via optical microscopy the nucleation kinetics of barium disilicate spherulites in BaO–SiO₂ glasses containing 27.0–33.3 mol% BaO undergoing isothermal treatments at 718–760°C. Amorphous phase separation in these two glasses was monitored by SAXS and transmission electron microscopy (TEM). The average diameter, number, and surface area of amorphous droplets were obtained as a function of time at 743 and 760°C. In glasses that did not show amorphous phase separation, the crystal nucleation rate, I , was constant at a given temperature. In glasses undergoing liquid phase separation, I increased with time approaching a constant value, identical for phase-separated glasses with different compositions. There was a striking correlation between

the time required to reach a constant value of I and the time required to attain the equilibrium composition of the amorphous (baria-rich) matrix phase, as revealed by a constant integrated SAXS intensity. The crystal nucleation rate, I , depended primarily on the composition of the baria-rich phase. There was no apparent relationship between I and either the surface area or the number of droplets.

Our results clearly demonstrated that the role of the interfaces between the liquid phases in crystal nucleation is very small due to the small interfacial energy between the liquid phases and, hence, the compositional shift of the glassy matrix caused by LLPS is the main factor responsible for the enhancement of crystal nucleation and growth. We believe this result is now the most accepted explanation for the effects of LLPS on crystallization. At present, there is very limited activity on this subject, with the exception of some members of the metallic glass community who are still debating the reason.

On the Validity of the Classical Nucleation Theory

Next, again with Peter James, we tested the validity and applicability of the classical nucleation theory (CNT) in different ways using various glasses over several years; this study is not yet finished!^{7–14}

In the first part of the research study,⁷ we assumed a constant value of nucleus/liquid surface energy, σ , and that the activation enthalpy for atomic jumps at the liquid/crystal nucleus interface (ΔG_d) was similar to that for viscous flow (ΔG_η), an assumption also adopted by other authors. We found a large discrepancy of 30–55 orders of magnitude between the experimental nucleation rates and the theoretical values, although the temperature dependence was well described by theory!

In a subsequent study,⁸ with Michael Weinberg (another *G. W. Morey* awardee), an original, more rigorous approach was proposed and tested using transient times for nucleation instead of using the viscosity to calculate ΔG_d . Again, large discrepancies were found in the magnitude and now also in the temperature dependence of the nucleation rates for four glasses.

Then, continuing the collaboration with Michael Weinberg, the most severe assumption of CNT, *that is*, the postulate that the interfacial energy does not depend on nucleus size, $\sigma = \sigma_\infty$, was tested.⁹ In this

1 case, the Tolman expression for $\sigma(r)$ was incorporated
2 into CNT, but two fitting parameters were needed
3 (Tolman's parameter, λ , and σ_∞) instead of only a
4 fixed value of the surface energy, σ_∞ , which had been
5 used in previous tests. An impressive agreement
6 between theory and experiment was found for this
7 method. However, in all tests, neither σ_∞ nor $\sigma(r)$
8 could be determined independently and had to be fit-
9 ted by forcing the temperature of the experimental and
10 theoretical maxima to coincide.

11 Other related studies have been conducted with
12 the invaluable help of graduate students, as well as Vla-
13 dimir Fokin and Jörn Schmelzer. In one such work,¹¹
14 we showed that to obtain a reasonable value of σ , it
15 was necessary to reduce the thermodynamic driving
16 force from the classical value used for the macrophase.
17 This result indicated that the volume properties of criti-
18 cal nuclei may differ from the volume properties of the
19 macro phase.

20 In several studies, we discussed the assumption of
21 CNT that the properties of the critical nuclei and mac-
22 rophases are equal. However, CNT could, in principle,
23 be modified to incorporate the nucleus size dependence
24 of the surface energy and the driving force. Hence, after
25 all of our findings, we propose that the main question
26 should not focus on the validity of CNT, but it should
27 instead consider the usefulness of CNT for describing
28 real experiments with complex systems. In other words,
29 do such systems satisfy the CNT model? However, for
30 a definitive answer, the independent determination of
31 $\sigma(r, T)$ would be necessary. Several scientists around the
32 world are still pursuing this objective, and this field is
33 thus open for further exploration.

34 35 36 **Metastable Phases and Mutant Crystals in Glasses**

37
38 Before an ultimate test of any nucleation theory is
39 performed, it is essential to confirm or discard the pos-
40 sibility of the precipitation of metastable phases in the
41 early stages of nucleation, because, in principle, if con-
42 firmed, the metastable phases could perhaps explain the
43 above-described discrepancy between the predictions
44 obtained using CNT and the experimental nucleation
45 rates. We have carried out a few studies on this subject
46 with several Brazilian students, especially Paulo Soares,
47 as well as Pierre Lucas (then a graduate student) and
48 with Michael Weinberg. In a related set of studies
49 carried out by other Brazilian students with Vladimir

Fokin and Russian colleagues, we have shown that,
even in stoichiometric glasses, a crystal phase that is
enriched or depleted in some component (in relation to
the expected stoichiometric crystal) may precipitate in
the early stages of crystallization and that its composi-
tion changes with the evolution of the crystallization
process (mutant crystals).^{15–23}

In previous studies,^{15,16} we considered findings
about metastable phase formation in lithium disilicate
glass $\text{Li}_2\text{O}-2\text{SiO}_2$ (LS_2) and its effects on the crystalliza-
tion of the stable LS_2 crystal phase. The early crystalli-
zation stages of slightly substoichiometric LS_2 glasses
were probed with both SAXS and selected area diffraction
(SAD). Then, we carefully measured the crystal
nucleation rate (I), the growth rate (U), the time evolu-
tion of crystallinity, and the apparent induction period
(τ) for crystal nucleation and growth at 500°C
($T_g \sim 450^\circ\text{C}$). Finally, the kinetic parameters I and U
were used in a modified form of the Johnson-Mehl-
Avrami-Kolmogorov-Yeerofev (JMAKY) equation, which
also accounted for transient nucleation conditions, to
test the nucleation mechanism. Depending on the heat
treatment, one or more metastable phases indeed pre-
cipitated in the early crystallization stages of LS_2 glass;
however, these phases did not play a significant role in
the crystallization mechanism of the thermodynamically
stable LS_2 phase.

In another study,²² the relative frequency of occur-
rence of two phases — LS (metastable) and LS_2 (sta-
ble) — was monitored as a function of heat treatment
time. Despite the poor statistics (on average, only a
dozen crystals were detected in the TEM samples for
each treatment time), we observed that with treatment
for up to 20 h at 454°C , the relative number of LS
crystals was larger than that of LS_2 . The number of LS
crystals decreased with increasing treatment time, but,
despite the decreasing LS/ LS_2 ratio, LS crystals were
still present after 120 h (<0.01 crystallized volume frac-
tion). After 312 h (3 vol.% crystallized fraction), only
the stable LS_2 phase was observed (it should be stressed
that the nucleation time lag at this temperature is only
1–2 h). Here, one should consider that all detected
crystals had sizes of approximately 500 nm, *that is*,
they were much larger than the critical nucleus size.
Thus, these data all refer to the initial stage of overall
crystallization, but for a relatively advanced stage of
nucleation. These results showed that both phases coex-
isted in the early stages of crystallization in glasses with
a composition similar to that of lithium disilicate.

Therefore, the following two possible situations could occur:

1. There is simultaneous homogeneous nucleation of the LS_2 and LS phases, but the LS phase disappears at some point during the heat treatment. In this case, LS is a metastable phase that does not affect the nucleation path of LS_2
2. The LS crystals nucleate first, and then the LS_2 crystals nucleate heterogeneously over the LS. This mechanism could partially explain the failure of the classical nucleation theory.

Regarding the “mutant” crystals phenomenon, data were collected on the bulk crystallization kinetics of a glass with a composition very close to the stoichiometric phase $Na_2O.2CaO.3SiO_2$.^{17,21,23} The effects of pre-existing crystals on the nucleation and growth behavior of secondary crystals were described for the first time. Primary crystals, grown at high temperatures, dramatically *hindered* the formation of new crystals in their vicinity at lower temperatures (the courtyard effect). The crystal growth velocity decreased with increasing crystal size. Chemical analysis by energy-dispersive X-ray spectroscopy demonstrated that the above-mentioned effects resulted mainly from compositional changes to the glass matrix near the primary crystals. Extrapolating the curve of crystal composition versus size down to size zero allowed us to estimate the critical crystal composition and conclude that the primary crystals were far from stoichiometric.

A detailed discussion on the roles of metastable phases in nucleation can be found in a review article.²⁴ So far, our work with these two systems has established that in the initial nucleation stages, the clusters are solid solutions (ss) with a $Li_2O.2SiO_2$ structure but are enriched in Li and are ss with an $Na_2O.2CaO.3SiO_2$ structure but enriched in Na. This fact does not contradict the conclusions of the previous studies. In summary, metastable and transitory phases indeed appear in some glasses, but apparently these phases do not explain the large discrepancies in CNT!

The Validity of the JMAKY Theory

An adequate description of the overall crystallization kinetics is of utmost importance.^{25–31} In 1988, we carried out one of the first rigorous tests of the JMAKY theory of transformation kinetics, with no adjustable

parameters, for homogeneous nucleation in a glass.²⁵ First, we measured the crystal nucleation and growth rates in a stoichiometric $1Na_2O.2CaO.3SiO_2$ glass and then calculated the expected evolution of the volume fraction crystallized using the JMAKY equation and compared it to measured values. At that time, we did not know that the crystal composition differs somewhat from that of the parent glass in the early stages. We nevertheless demonstrated that, if proper precautions are taken when determining the nucleation and growth rates, the JMAKY theory describes exceptionally well the time evolution of the overall crystallization of stoichiometric glasses.²⁵

We also used the JMAKY equation to calculate the volume fraction transformed in nonisothermal situations and for small spherical glass particles (in addition to the normally assumed case of infinitely large glass samples).^{27,31}

In summary, if the assumptions of the JMAKY equation are respected, it describes quite well the isothermal and nonisothermal crystallization kinetics of stoichiometric glasses.

Homogeneous Versus Heterogeneous Nucleation in Glasses

Next, from 1987 to 2003, with the invaluable insight of Eberhard Muller, Mike Weinberg and Vladimir Fokin, we were devoted to answering the following question: *Why is a thermodynamically unfavorable mechanism — homogeneous nucleation — experimentally observed in some glasses?* A series of papers^{32–36} was published on this particular problem in that period.

In one of our first studies, in 1987,³² we demonstrated that a simple rule of thumb can be used to distinguish the nucleation mechanism in stoichiometric glass-forming systems. For compositions that have small values of reduced glass transition temperatures ($T_g/T_f < 0.6$), the temperatures of the maximum nucleation rates, T_{max} , are higher than the T_g values and these systems exhibit homogeneous (internal) nucleation in laboratory time scales. Conversely, for the majority of glasses, the typical values of the reduced T_g are higher ($T_g/T_f > 0.6$), and the calculated (by CNT) values of T_{max} are significantly below T_g ; only heterogeneous nucleation is observed in typical laboratory tests. To the best of our knowledge, no exception to this remarkable trend has been reported so far.

In a second study,³³ we showed that the failure to experimentally detect homogeneous nucleation in glasses for which $T_{\max} < T_g$ is due to one or both of the following causes: nucleation or growth rates that are too low, or long induction times for nucleation in temperature ranges for which the predicted (by CNT) steady-state homogeneous nucleation rates are expected to be significant.

Next,³⁵ we showed that the mass densities of glasses that nucleate homogeneously are similar to those of their crystal phases, while those of glasses that only nucleate heterogeneously could be similar to or quite different from the densities of equivalent isochemical crystals (Table I).

Hence, structural similarity is a necessary, but not sufficient, condition for substantial homogeneous nucleation rates. It should be stressed that the density misfit is not a unique factor that determines the nucleation rates. For instance, the difference in I_{\max} between CaO.SiO₂ and Li₂O.SiO₂ glasses is approximately three orders of magnitude, whereas density misfit differs only by a factor of approximately 50%.

Table I. Densities of Glass and Isochemical Crystal Phases (g/cm³)

System	Glass	Crystal	$\Delta\rho/\rho_{\text{glass}}(\%)$
Homogeneous nucleation			
BaO.2SiO ₂	3.72	3.77–3.73	1.3/0.3
Na ₂ O.2CaO.3SiO ₂	2.75	2.80	1.8
CaO.Al ₂ O ₃ .2SiO ₂	2.70	2.76	2.2
Na ₂ O.SiO ₂	2.56	2.62	2.3
2Na ₂ O.CaO.3SiO ₂	2.66	2.76	3.8
Li ₂ O.2SiO ₂	2.35	2.45	4.3
CaO.SiO ₂	2.90	3.09	6.6
Li ₂ O.SiO ₂	2.34	2.52 (ort)	7.7
Extremely low nucleation rates or only heterogeneous nucleation			
K ₂ O.2SiO ₂	2.47	2.46–2.53	0.6/2.4
Na ₂ O.2SiO ₂	2.49	2.39–2.56	3.7/3.1
PbO.SiO ₂	5.98	6.49	8.5
As ₂ S ₃	3.17	3.46	9.1
P ₂ O ₅	2.37	2.72	14.8
Na ₂ O.Al ₂ O ₃ .6SiO ₂	2.28	2.62	14.9
GeO ₂	3.65	4.23 (hex)	15.9
CaO.MgO.2SiO ₂	2.70	3.20	18.5
B ₂ O ₃	1.84	2.46	33.7

We then showed³⁶ that the maximum values of nucleation rates, I_{\max} , scale with the reduced glass transition temperature, $T_{gr} = T_g/T_m$. This article provided experimental and theoretical evidence for the correlation between I_{\max} and T_{gr} for 51 glass-forming liquids. In addition, it demonstrated an analogous correlation between the time lag of nucleation at T_{\max} and T_{gr} .

In summary, if the density difference between a given glass and its isochemical crystalline phase is large, say >10%, it will only nucleate heterogeneously. If the densities are comparable, nucleation could be homogeneous, but this condition alone is not sufficient to ensure this nucleation mechanism (or a high and detectable nucleation rate). Based on these results, we started to think at possible structural relationships between the nucleation mechanism and at the similarity between the molecular structure of the parent glass and its crystal phase. Such studies are described below.

Molecular Structure Versus Nucleation Mechanism

We then decided to test whether the predominant nucleation mechanism (or the homogeneous nucleation rates) of a given glass composition could be correlated with the extent of structural similarity at the local and intermediate-range level between the glass and the crystal phase to which it transforms.^{37–43} In 1992, we started with a simple test to check whether the local modifier cation arrangements in the glass were similar to those in their corresponding crystal phases in systems that nucleated homogeneously, whereas the modifier cation structures of the glass and crystal phases of compositions that only nucleated heterogeneously were quite distinct.³⁷ Following that study, we continued to search for similarities/dissimilarities at the intermediate-range order, that is, at the linkages between SiO₄ tetrahedra, which form the basic units of silicate glasses and their isochemical crystals, and the nucleation mechanism.

In another study,³⁸ the short-range order of several silicate glasses that nucleate homogeneously in their volume (CaO.SiO₂, Na₂O.SiO₂, Li₂O.SiO₂, Li₂O-2SiO₂, BaO.2SiO₂ and CaO.Al₂O₃.2SiO₂) as well as that of glasses that only nucleate heterogeneously on their external surfaces or in volume with the addition of nucleating agents (PbO.SiO₂, Na₂O.2SiO₂, CaO.MgO.2SiO₂, K₂O.TiO₂.3SiO₂ and Na₂O.Al₂O₃.6SiO₂) was analyzed and compared with the structures

of their equilibrium isochemical crystalline phases. We showed that for glasses displaying measurable homogeneous nucleation rates, both the cationic and anionic arrangements in glass and isochemical crystal are similar. For the second family of glasses, the structures of a glass and its isochemical crystal significantly differ, and only heterogeneous nucleation was observed. However, we later found several exceptions to this trend! We have been working on this particular problem with Eberhard Muller, Klaus Heide, José Schneider, Adrian Wright (another *G. W. Morey* winner), Natalia Vedishva, the late Boris Schatmakim, Josef Zwanziger, and students having published a few articles over the last 20 years.

For instance, we tested³⁹ the possible existence of a relationship between the similarity of the local structure of the network-forming cation Si^{4+} (considering Q^n units and chemical shifts) in glasses and isochemical crystals, and the nucleating ability of some glasses. Four metasilicate glasses with widely different homogeneous internal nucleation rates — $\text{Na}_2\text{Ca}_2\text{Si}_3\text{O}_9$ and $\text{Na}_4\text{CaSi}_3\text{O}_9$ (very large nucleation rates), CaSiO_3 (intermediate) and $\text{CaMgSi}_2\text{O}_6$ (undetected small) — were chosen. We obtained magic angle spinning nuclear magnetic resonance spectroscopy (MAS-NMR) data for $\text{Na}_2\text{Ca}_2\text{Si}_3\text{O}_9$ and $\text{Na}_4\text{CaSi}_3\text{O}_9$ glasses and their respective isochemical crystalline phases for the first time. Additionally, we repeated the NMR measurements of glasses and crystals that were previously studied by other authors (CaSiO_3 and $\text{CaMgSi}_2\text{O}_6$) to test the consistency of our experimental techniques and analytical method.³⁹ Different central chemical shifts of Q^2 resonances in parent glasses and their isochemical crystals were measured, thus indicating structural differences. The relative amount of Q^n groups in each glass was obtained from the deconvolution of the ^{29}Si MAS-NMR spectra. The shape of the Q^n distribution for each system was considered a measure of the similarity of the connectivities of SiO_4 tetrahedra in each glass with respect to its isochemical metasilicate crystal (which has only Q^2 groups). A correlation was found between the shape of the Q^n distribution and the nucleation tendency of these glasses, indicating that similarities between the tetrahedra connectivities in a glass and its isochemical crystal may play a role in determining the internal nucleation tendency of the metasilicate glasses studied.

Relatively little information was available to test our structural similarity hypothesis because of the lack

of long-range periodicity in glass and the absence of effective analysis methods. Hence, in another work,⁴² $\text{Li}_2\text{O}\cdot 2\text{B}_2\text{O}_3$ (L2B) and $\text{Na}_2\text{O}\cdot 2\text{B}_2\text{O}_3$ (N2B) glasses, which exhibit homogeneous (internal) and heterogeneous (surface) devitrification mechanisms, respectively, and their corresponding crystals were prepared and studied using multiple solid-state NMR techniques. Of those techniques, ^{11}B MAS and MQMAS (multi-quantum-magic-angle-spinning) experiments were applied to reveal short-range order information; ^7Li and ^{23}Na spin-echo decay and $^{11}\text{B}\{^6\text{Li}\}$ and $^{11}\text{B}\{^{23}\text{Na}\}$ rotational-echo double-resonance (REDOR) experiments were used to determine homonuclear and heteronuclear interactions that can reflect the intermediate-range order. We found that the local bonding environments of the L2B crystal and glass are quite similar, whereas there are significant differences in the N2B system. Moreover, the experimental results indicated that the second moment (M_2) values of both homo- and heterodipolar interactions measured for the L2B glass are very close to those of its isochemical crystal. In contrast, the M_2 values for N2B glass differ significantly from those of its crystal phase. These observations indicate the existence of a strong correlation between structural similarity at both the short and intermediate length scale, and nucleation mechanism.

Let us then consider two extreme cases. (i) The structure of the liquid is very close to that of its crystal form. Then, the necessary structural reorganization for crystallization is facilitated due to the reduction in the kinetic barrier for nucleation and growth, but the thermodynamic driving force will be weak. (ii) The structure of the liquid strongly differs from that of its crystal. This case corresponds to a high kinetic and low thermodynamic barrier. Because the similarity of the liquid and crystal structures affects the kinetic and thermodynamic aspects of crystallization in different ways, the final result is determined by the interplay of these factors. In any case, as the number of systems studied thus far is quite small and some exceptions to the expected structure versus nucleation relationship have been reported, this remains an open problem that deserves further attention.

Surface Crystallization

About 20 years ago, our research group started to focus on establishing the mechanisms and kinetics of

1 crystal nucleation and growth on free glass surfaces (by
2 far the most common devitrification mechanism).
3 Jointly with several graduate students, especially Nora
4 Mora, we published several papers on this subject
5 between 1991 and 2000.^{44–51} We also significantly
6 benefited from useful discussions carried out in the
7 framework of the TC7 — the Crystallization Commit-
8 tee of the ICG. Here, we should mention a fruitful col-
9 laboration work with three TC7 members: Miguel
10 Prado, Vladimir Fokin, and Ralf Muller. Some of our
11 papers catalyzed interest on the subject, and we believe
12 that they were important for the development of some
13 sintered glass-ceramics, described later in this review.

14 Based on our results, we concluded that in most
15 cases, surface nucleation is triggered by a certain num-
16 ber of impurity sites, the number of which depends on
17 the degree of surface perfection and cleanliness. High
18 surface nucleation rates are due to the low interfacial
19 energy between the contaminants existing at the glass
20 surface and the crystal nuclei. Our findings on the fac-
21 tors controlling the mechanisms and kinetics of surface
22 crystallization were fundamental in moving to the next
23 two problems: (i) glass-forming ability and (ii) viscous
24 sintering of glass particles with concurrent surface crys-
25 tallization.

26 27 28 **Glass-Forming Ability (on cooling) Versus Glass** 29 **Stability (on heating)**

30
31 We have carried out a good deal of research in col-
32 laboration with *G. W. Morey* winner Donald Uhlmann
33 on the fundamental problem of the glass-forming abil-
34 ity of different liquid systems.^{52,53} We also developed
35 some systematic studies that unveiled the parameters
36 (combinations of DSC characteristic temperatures) that
37 are best able to describe glass stability against devitrifi-
38 cation (on heating), and its correlation with the glass-
39 forming ability of a certain liquid (upon cooling) for
40 oxide liquids.^{54–61} These studies started with the com-
41 petent work of former students and postdocs Aluísio A.
42 Cabral, Marcio F. Nascimento, and Eduardo B. Ferre-
43 ira and continued more recently in collaboration with
44 Richard Brow (*G. W. Morey* awardee) and his group in
45 Rolla, Missouri.

46 We re-evaluated, for instance, nine parameters of
47 glass stability against crystallization determined from
48 differential scanning calorimetry (DSC) experiments to
49 predict the glass-forming ability of oxide liquids on

cooling.⁶¹ The GS parameters were calculated using
characteristic glass transition, crystallization, and melt-
ing peaks of DSC thermograms. Using lithium borate
glasses, we found that seven stability parameters gave
similar trends for compositions up to 33.3 mol% lithia,
where, as we expected, GS significantly decreases with
lithia content. Thereafter, up to 66.7 mol% lithia, GS
was approximately constant, thereby indicating that,
surprisingly, the composition does not significantly
affect the GFA within this wide compositional range.
This result qualitatively agrees with our experience of
successfully preparing glasses with compositions of up
to 74 mol% lithia. The above-cited article⁶¹ corrobo-
rates our previous studies^{55,56,58} showing the adequacy
of simple DSC tests to comparatively gauge the GS
and GFA of glass-forming liquids.

Finally, our research work demonstrated that, for
the most common cases, GFA depends on hetero-
geneous nucleation (that is very difficult to control),
whereas GS may depend on both homo- and heteronu-
cleation, and both GFA and GS depend on the crystal
growth rate.

Sintering with Concurrent Crystallization

Using our accumulated experience on surface crys-
tallization processes, we started to conduct a systematic
study on glass sintering with concurrent surface crys-
tallization.^{62–73} This topic is a matter of keen interest
because one could, in principle, produce all sorts of
complex-shaped monolithic glasses and glass-ceramics
by sintering powdered glasses. The key issue here is to
obtain viscous flow sintering before surface crystalliza-
tion takes over and imparts densification. Of special
importance is one of the last papers in the series⁷¹ that
proposes and successfully tests a useful sinterability
parameter. Some conclusive and practical results on this
subject are summarized in a few papers coauthored by
Miguel Prado, Ralf Muller, Catia Fredericci, Viviane
Oliveira, Raphael Reis, in addition to our Spanish col-
laborators Alicia Duran and Maria Jesus Pascual, and
several students.

We critically discussed the main glass sintering
models — Frenkel's, Mackenzie-Shuttleworth's, Scherer's
and our own *Clusters* model — and focused on the
problem of sintering with concurrent crystallization
in a review paper.⁶⁹ The *Clusters* model was tested
for compacts of spherical soda-lime-silica (SLS) glass

particles that have a narrow size distribution and easily crystallize. Simulations for isothermal and nonisothermal sintering with simultaneous crystallization were compared with experimental data. Physical and processing parameters, such as viscosity, surface tension, crystal growth rate, number of nucleation sites, particle size distribution, and particle packing, are considered in the model. The evolution of the relative density during sintering and the pore size distribution in the final stages of sintering were reasonably predicted by the model. All results were discussed considering the assumptions made and other complicating factors, such as compositional shifts due to crystallization, temperature gradients, and degassing. Finally, we discussed the physical and processing parameters that determine whether sintering is more favorable than crystallization. We demonstrated that the *Clusters* model can describe the densification of devitrifying glass compacts for any particle size distribution.

In another study,⁶⁴ we evaluated all the previous publications and demonstrated that the *Clusters* model and related algorithm provide a powerful simulation tool for calculating or designing the isothermal or nonisothermal densification of devitrifying or stable glass compacts with any particle size distribution, thus minimizing the number of time-consuming laboratory experiments.

The recent PhD thesis⁷³ of our student Raphael Reis demonstrated that some fine details of the *Clusters* model must be corrected to give an even more precise description of the sinter-crystallization process in the final stages of densification. All of the required parameters (viscosity, crystal growth rates, number of active nucleation surface sites, glass-air surface energy, and particle size distribution) for simulating the sinter-crystallization processes of spherical particles can be independently measured, but one as yet unsolved problem is how to account for the odd shape of milled glass particles.

In conclusion, there are a number of open issues regarding the sinter-crystallization phenomenon that still need to be resolved.

Diffusion Processes Controlling Crystal Nucleation and Growth

More recently, our team, led by former postdocs Marcio Nascimento and Eduardo Ferreira, once more in collaboration with Vladimir Fokin, started to look in detail into the diffusion processes that control

crystal nucleation, crystal growth, and viscous flow. Our research group also examined the old-standing controversy regarding the possible breakdown of the Stokes–Einstein–Eyring (SEE) equation at sufficiently low temperatures near T_g .^{74–85}

In one article,⁷⁷ we analyzed extensive literature data on crystal growth rate and viscosity in the temperature range between $1.1 T_g$ (glass transition temperature) and the melting point of silica, T_m . We selected data for one silica glass type, the samples of which had similar impurity contents, and confirmed that the normal growth model describes quite well the experimental growth rate data in this wide undercooling range. We then calculated the effective diffusion coefficients from crystal growth rates, D_w , and from viscosity, D_η (using the SEE equation), and compared these two independent diffusivities with the directly measured self-diffusion coefficients of silicon and oxygen in the same silica glass for which viscosity was measured. Our results showed that silicon (but not oxygen) controls the diffusion dynamics involved in both crystal growth and viscous flow in undercooled silica.

Next, we evaluated⁸⁴ the kinetic coefficients of crystal growth for nine undercooled glass-forming liquids, in a wide temperature range, from slightly below the melting point down to the glass transition region T_g , thus covering a wide viscosity range: $\eta = 10^1$ – 10^{13} Pa.s. Viscosity was able to describe the transport part of crystal growth rates from low to moderate viscosities ($\eta < 10^6$ Pa.s), and hence, we demonstrated that the SEE equation works well in this viscosity range for all systems tested. For strong glasses, the SEE equation works well from low to high viscosities, from the melting point down to T_g ! However, for at least three fragile liquids — diopside (kink at $1.1 T_g$, $\eta = 1.6 \times 10^8$ Pa.s), lead metasilicate (kink at $1.1 T_g$, $\eta = 4.3 \times 10^6$ Pa.s), and lithium disilicate (kink at $1.1 T_g$, $\eta = 1.6 \times 10^8$ Pa.s) — there were clear signs of a breakdown in the SEE equation at these high viscosities. These results confirmed that viscosity data cannot be used to describe the transport part of the crystal growth in fragile glasses near T_g .

We also assessed⁸⁵ extensive literature data on viscous flow, crystal nucleation, and growth, in $\text{Li}_2\text{O}\cdot 2\text{SiO}_2$, over a wide temperature range, from above T_m to $0.98 T_g$ where $T_g \approx 727$ K is the calorimetric glass transition temperature and $T_m=1307$ K is the melting point. We then calculated the diffusion coefficients controlling crystal growth, D^U , and viscous flow, D^l ,

1 and compared with the ionic diffusion coefficients of
2 Li^+ , O^{2-} , and Si^{4+} obtained from experiments and
3 molecular dynamic simulations. These values were then
4 employed to estimate the effective volume diffusion
5 coefficients, D_{eff}^V , resulting from their combination
6 within a hypothetical $\text{Li}_2\text{Si}_2\text{O}_5$ “molecule”. The simi-
7 larity in the temperature dependencies of $1/\eta$ and D_{eff}^V
8 corroborated the validity of the SEE equation at high
9 temperatures around T_m . Using the equality of D_{eff}^V
10 and D^l , we estimated the jump distance $\lambda = 2.70 \text{ \AA}$
11 from the SEE equation and showed that the values of
12 D^U have the same temperature dependence but exceed
13 D^l by about eightfold. The difference between D^l and
14 D^U indicates that the former represents the process of
15 mass transport in the bulk, whereas the latter relates to
16 the mobility of the structural units on the crystal/liquid
17 interface. We then employed the values of $\eta(T)$
18 reduced by eightfold to calculate the growth rates U
19 (T). The resultant $U(T)$ curve was consistent with
20 experimental data down to a decoupling temperature
21 $T_d^U \approx 1.1\text{--}1.2 T_g$, when D^l started to decrease with
22 decreasing temperature faster than D^U . A similar decou-
23 pling occurred between D^l and D^r (estimated from
24 nucleation time-lags) but at a lower temperature
25 $T_d^r \approx T_g$. The different behaviors of $D^r(T)$ and D^U
26 (T) are likely caused by differences in the mechanisms
27 of critical nuclei formation and growth. Therefore, we
28 showed that in the deeply supercooled liquid state
29 below T_d , mass transport for crystal nucleation and
30 growth are not controlled by viscosity. The origin of
31 decoupling was assigned to spatial *dynamic heterogeneity*
32 in glass-forming melts.

33 Overall, our results indicated no breakdown of the
34 SEE equation from the liquidus down to $T \sim 1.15 T_g$
35 but with clear signs of a decoupling of viscosity and
36 crystallization processes at deeper undercoolings for
37 fragile glasses. However, no decoupling has been found
38 for strong Q^4 glasses. This breakdown or decoupling is
39 likely due to dynamic heterogeneities in undercooled
40 glass-forming liquids. Future studies should focus on at
41 what happens at even deeper undercoolings, from
42 $1.15 T_g$ down to approximately $0.9 T_g$.

43 Review Papers

44 Summarizing the above list of original research, we
45 have also authored some review papers. In the most
46 extensive of these papers,²⁴ we evaluated the relevant

47 results from the experiments of our group and those of
48 other authors on the internal homogeneous crystal
49 nucleation in silicate glasses obtained from 1965 to
2005 and their analyses in the framework of classical
nucleation theory (CNT). Particular attention was
devoted to studying the properties of the critical nuclei,
which, to a large extent, govern nucleation kinetics.
The basic regularities of both the time and temperature
dependencies of nucleation rates were illustrated using
experimental data. Special attention was given to seri-
ous problems that arise in the quantitative description
of nucleation rates when using CNT. These problems
include the dramatic discrepancy between calculated
and measured nucleation rates; the high value of the
crystal nuclei/melt surface energy compared with the
expected value estimated via Stefan’s rule; the increase
in σ with increasing temperature; and the discrepancies
between the values of the surface energy and the time
lag for nucleation when independently estimated from
nucleation and growth kinetics. As we discussed previ-
ously, analyzing the above-mentioned problems led to
the following conclusion: in contrast to Gibbs’ descrip-
tion of the heterogeneous systems underlying CNT, the
bulk thermodynamic properties of the critical nuclei
generally differ from those of the corresponding macro-
phase, thus resulting simultaneously in significant dif-
ferences of the surface properties compared with the
respective parameters of the planar interfaces. In partic-
ular, direct experimental evidence was presented for
compositional changes of the crystal nuclei during the
formation of critical nuclei and their growth from criti-
cal to macrosizes. In addition, a detailed examination
of crystal nucleation and growth kinetics showed a
decrease both in the thermodynamic driving force for
nucleation and in the critical nuclei/liquid interfacial
energy, compared with the respective properties of the
macrophase.

43 Summary

44 The specific conclusions about each research topic
45 investigated were stated at the end of each section. The
46 research described above comprises a sequential sam-
47 pling of insights and advances vital to the understand-
48 ing of some relevant scientific issues related to the
49 nature, mechanisms, and kinetics of glass crystallization.
Our philosophy has been to focus on a few relevant
problems for several years at the deepest possible level.

We suppose that most of the articles described were innovative and led to some advancement of the knowledge of key aspects of phase transformations in glasses. However, there is still a great scope of further study in both the scientific and technological aspects of glass crystallization!

Acknowledgments

I am indebted to Austen Angell for fruitful discussions over the last 10 years and especially for nominating me for the *G. W. Morey* award. I also thank David Pye for inviting and encouraging me to write this review article; Vladimir Fokin for his invaluable partnership, discussions, and critical comments; and M.O. Prado, M.L.F. Nascimento, O. Peitl, E.B. Ferreira, L.B. Glebov, J. Lumeau, V.R. Mastelaro, J.W.P. Schmelzer, M.C. Weinberg⁺, C. Fredericci, A.A. Cabral, G.P. Souza, P.F. James⁺, P.C. Soares, J.W. Zwanziger, F.C. Serbena, A.C.M. Rodrigues, J.F. Schneider, A.F. Craievich, L.L. Hench, R.K. Brow, D.R. Uhlmann, R. Müller and numerous other coauthors for their most useful insights along all these years. Finally, I thank the Brazilian funding agencies Fapesp, CNPq and Capes for their generous funding.

References

1. E. D. Zanotto, "Glass Crystallization Research – A 36-Year Retrospective. Part II, Methods of Study and Glass-Ceramics," *Int. J. Appl. Glass Sci.*, ???-????-???? (2013) submitted.
2. E. D. Zanotto and A. F. Craievich, "The Role of Amorphous Phase-Separation in Crystal Nucleation in Splat Cooled $\text{Li}_2\text{O-SiO}_2$ Glasses," *J. Mater. Sci.*, 16 [4] 973–982 (1981).
3. E. D. Zanotto, A. F. Craievich, and P. F. James, "SAXS and TEM Studies of Phase-Separation in BaO-SiO_2 Glasses," *J. de Physique*, 43 [NC 9] 107–110 (1982).
4. A. F. Craievich, E. D. Zanotto, and P. F. James, "Kinetics of sub-Liquidus Phase-Separation in Silicate and Borate Glasses – A Review," *Bulletin de Mineralogie*, 106 [1–2] 169–184 (1983).
5. S. Bras, A. Craievich, J. M. Sanchez, C. Williams, and E. D. Zanotto, "Small-Angle x-ray-Scattering Study of Phase-Separation in Glasses Using a new Position-Sensitive Detector," *Nucl. Instrum. Methods Phys. Res.*, 208 [1–3] 489 (1983).
6. E. D. Zanotto, P. F. James, and A. F. Craievich, "The Effects of Amorphous Phase-Separation on Crystal Nucleation Kinetics in BaO-SiO_2 Glasses. 3. Isothermal Treatments at 718°C to 760°C - Small-Angle x-ray-Scattering Results," *J. Mater. Sci.*, 21 [9] 3050–3064 (1986).
7. E. D. Zanotto and P. F. James, "Experimental Tests of the Classical Nucleation Theory for Glasses," *J. Non-Cryst. Solids*, 74 [2–3] 373–394 (1985).
8. M. C. Weinberg and E. D. Zanotto, "Re-Examination of the Temperature-Dependence of the Classical Nucleation Rate - Homogeneous Crystal Nucleation in Glass," *J. Non-Cryst. Solids*, 108 [1] 99–108 (1989).
9. M. C. Weinberg, E. D. Zanotto, and S. Manrich, "Classical Nucleation Theory With a Size Dependent Interfacial-Tension - $\text{Li}_2\text{O}_2\text{SiO}_2$ Crystal Nucleation," *Phys. Chem. Glasses*, 33 [3] 99–102 (1992).
10. V. M. Fokin and E. D. Zanotto, "Crystal Nucleation in Silicate Glasses: The Temperature and Size Dependence of Crystal/Liquid Surface Energy," *J. Non-Cryst. Solids*, 265 [1–2] 105–112 (2000).
11. V. M. Fokin, E. D. Zanotto, and J. W. P. Schmelzer, "Method to Estimate Crystal/Liquid Surface Energy by Dissolution of Subcritical Nuclei," *J. Non-Cryst. Solids*, 278 [1–3] 24–34 (2000).
12. A. A. Cabral, V. M. Fokin, E. D. Zanotto, and C. R. Chinaglia, "Nanocrystallization of Frenote Glass. I. Nucleation and Growth Kinetics," *J. Non-Cryst. Solids*, 330 [1–3] 174–186 (2003).
13. A. A. Cabral, V. M. Fokin, and E. D. Zanotto, "Nanocrystallization of Frenote Glass. II. Analysis of Homogeneous Nucleation Kinetics," *J. Non-Cryst. Solids*, 343 [1–3] 85–90 (2004).
14. V. M. Fokin, E. D. Zanotto, J. W. P. Schmelzer, and O. V. Potapov, "New Insights on the Thermodynamic Barrier for Nucleation in Glasses: The Case of Lithium Disilicate," *J. Non-Cryst. Solids*, 351 [18] 1491–1499 (2005).
15. E. D. Zanotto and M. L. G. Leite, "The Nucleation Mechanism of Lithium Disilicate Glass Revisited," *J. Non-Cryst. Solids*, 202 [1–2] 145–152 (1996).
16. E. D. Zanotto, "Metastable Phases in Lithium Disilicate Glasses," *J. Non-Cryst. Solids*, 219 42–48 (1997).
17. V. M. Fokin, O. V. Potapov, C. R. Chinaglia, and E. D. Zanotto, "The Effect of pre-Existing Crystals on the Crystallization Kinetics of a Soda-Lime-Silica Glass. The Courtyard Phenomenon," *J. Non-Cryst. Solids*, 258 [1–3] 180–186 (1999).
18. L. L. Burgner, M. C. Weinberg, P. Lucas, P. C. Soares Jr, and E. D. Zanotto, "XRD Investigation of Metastable Phase Formation in $\text{Li}_2\text{O}_2\text{SiO}_2$ Glass," *J. Non-Cryst. Solids*, 255 [2–3] 264–268 (1999).
19. L. L. Burgner, P. Lucas, M. C. Weinberg, P. C. Soares Jr, and E. D. Zanotto, "On the Persistence of Metastable Crystal Phases in Lithium Disilicate Glass," *J. Non-Cryst. Solids*, 274 [1–3] 188–194 (2000).
20. P. C. Soares, P. A. P. Nascente, and E. D. Zanotto, "XPS Study of Lithium Disilicate Glass Crystallisation," *Phys. Chem. Glasses*, 43 [3] 143–146 (2002).
21. V. M. Fokin, O. V. Potapov, E. D. Zanotto, F. M. Spiandorello, V. L. Ugolkov, and B. Z. Pevzner, "Mutant Crystals in $\text{Na}_2\text{O}_2\text{CaO}_3\text{SiO}_2$ Glasses," *J. Non-Cryst. Solids*, 331 [1–3] 240–253 (2003).
22. P. C. Soares, E. D. Zanotto, V. M. Fokin, and H. Jain, "TEM and XRD Study of Early Crystallization of Lithium Disilicate Glasses," *J. Non-Cryst. Solids*, 331 [1–3] 217–227 (2003).
23. V. M. Fokin and E. D. Zanotto, "Continuous Compositional Changes of Crystal and Liquid During Crystallization of a Sodium Calcium Silicate Glass," *J. Non-Cryst. Solids*, 353 [24–25] 2459–2468 (2007).
24. V. M. Fokin, E. D. Zanotto, N. Y. Yuritsyn, and J. W. P. Schmelzer, "Homogeneous Crystal Nucleation in Silicate Glasses," *J. Non-Cryst. Solids*, 352 [26–27] 2681–2714 (2006).
25. E. D. Zanotto and A. Galhardi, "Experimental Test of the General-Theory of Transformation Kinetics - Homogeneous Nucleation in a $\text{Na}_2\text{O}_2\text{-CaO}_3\text{SiO}_2$ Glass," *J. Non-Cryst. Solids*, 104 [1] 73–80 (1988).
26. E. D. Zanotto and P. F. James, "Experimental Test of the General-Theory of Transformation Kinetics - Homogeneous Nucleation in a BaO_2SiO_2 Glass," *J. Non-Cryst. Solids*, 104 [1] 70–72 (1988).
27. E. D. Zanotto and M. C. Weinberg, "Saturation Effects in Homogeneous and Heterogeneous Crystal Nucleation," *J. Non-Cryst. Solids*, 105 [1–2] 53–62 (1988).
28. M. C. Weinberg and E. D. Zanotto, "Calculation of the Volume Fraction Crystallised in Nonisothermal Transformations," *Phys. Chem. Glasses*, 30 [3] 110–115 (1989).
29. E. D. Zanotto, "The Applicability of the General Theory of Phase Transformations to Glass Crystallization," *Thermochim. Acta*, 280 73–82 (1996).
30. A. C. M. Rodrigues, G. T. Niitsu, E. D. Zanotto, M. O. Prado, and V. M. Fokin, "Crystallization Kinetics of $\text{Na}_2\text{O}_2\text{CaO}_3\text{SiO}_2$ Glass Monitored by Electrical Conductivity Measurements," *J. Non-Cryst. Solids*, 353 [22–23] 2237–2243 (2007).

31. E. B. Ferreira, V. Lopez-Richard, E. D. Zanotto, and G. E. Marques, "Analytical Model for Heterogeneous Crystallization Kinetics of Spherical Glass Particles," *J. Am. Ceram. Soc.*, 92 [11] 2616–2618 (2009).
32. E. D. Zanotto, "Isothermal and Adiabatic Nucleation in Glass," *J. Non-Cryst. Solids*, 89 [3] 361–370 (1987).
33. E. D. Zanotto and M. C. Weinberg, "Trends in Homogeneous Crystal Nucleation in Oxide Glasses," *Phys. Chem. Glasses*, 30 [5] 186–192 (1989).
34. E. Meyer, E. D. Zanotto, and M. A. Aegerter, "Adiabatic Nucleation and Crystallization of Gels," *J. Non-Cryst. Solids*, 121 [1–3] 279–281 (1990).
35. E. D. Zanotto and E. Müller, "A Simple Method to Predict the Nucleation Mechanism in Glass," *J. Non-Cryst. Solids*, 130 [2] 220–221 (1991).
36. V. M. Fokin, E. D. Zanotto, and J. W. P. Schmelzer, "Homogeneous Nucleation Versus Glass Transition Temperature of Silicate Glasses," *J. Non-Cryst. Solids*, 321 [1–2] 52–65 (2003).
37. E. Müller, K. Heide, and E. D. Zanotto, "Influence of Cation Coordination on Nucleation in Silicate-Glasses," *Z. Kristallogr.*, 200 [3–4] 287–294 (1992).
38. E. Müller, K. Heide, and E. D. Zanotto, "Molecular-Structure and Nucleation in Silicate-Glasses," *J. Non-Cryst. Solids*, 155 [1] 56–66 (1993).
39. J. Schneider, V. R. Mastelaro, H. Panepucci, and E. D. Zanotto, "Si-29 MAS-NMR Studies of Qⁿ Structural Units in Metasilicate Glasses and Their Nucleating Ability," *J. Non-Cryst. Solids*, 273 [1–3] 8–18 (2000).
40. V. R. Mastelaro, E. D. Zanotto, N. C. Lequeux, and R. Cortes, "Relationship Between Short-Range Order and Ease of Nucleation in Na₂Ca₂Si₃O₉, CaSiO₃ and PbSiO₃ Glasses," *J. Non-Cryst. Solids*, 262 [1–3] 191–199 (2000).
41. J. Schneider, *et al.*, "Qⁿ Distribution in Stoichiometric Silicate Glasses: Thermodynamic Calculations and Si-29 High Resolution NMR Measurements," *J. Non-Cryst. Solids*, 325 [1–3] 164–178 (2003).
42. B. H. Chen, U. Werner-Zwanziger, M. L. F. Nascimento, and E. D. Zanotto, "Structural Similarity on Multiple Length Scales and its Relation to Devitrification Mechanism: A Solid-State NMR Study of Alkali Diborate Glasses and Crystals," *J. Phys. Chem. C*, 113 [48] 20725–20732 (2009).
43. B. Chen, U. Werner-Zwanziger, J. W. Zwanziger, M. L. F. Nascimento, L. Ghussn, and E. D. Zanotto, "Correlation of Network Structure With Devitrification Mechanism in Lithium and Sodium Diborate Glasses," *J. Non-Cryst. Solids*, 356 [44–49] 2641–2644 (2010).
44. E. D. Zanotto, "Surface Crystallization Kinetics in Soda Lime Silica Glasses," *J. Non-Cryst. Solids*, 129 [1–3] 183–190 (1991).
45. E. D. Zanotto, "Surface Nucleation in a Diopside Glass," *J. Non-Cryst. Solids*, 130 [2] 217–219 (1991).
46. N. Diaz-Mora, E. D. Zanotto, and E. C. Ziemath, "Crystal Nucleation Kinetics of a Metastable Phase on Cordierite Glass Surfaces," *Phys. Chem. Glasses*, 37 [6] 258–263 (1996).
47. E. C. Ziemath, N. Diaz-Mora, and E. D. Zanotto, "Crystal Morphologies on a Cordierite Glass Surface," *Phys. Chem. Glasses*, 38 [1] 1–5 (1997).
48. V. M. Fokin and E. D. Zanotto, "Surface and Volume Nucleation and Growth in TiO₂-Cordierite Glasses," *J. Non-Cryst. Solids*, 246 [1–2] 115–127 (1999).
49. N. Diaz-Mora, E. D. Zanotto, R. Hergt, and R. Müller, "Surface Crystallization and Texture in Cordierite Glasses," *J. Non-Cryst. Solids*, 273 [1–3] 81–93 (2000).
50. E. Wittman and E. D. Zanotto, "Surface Nucleation and Growth in Anorthite Glass," *J. Non-Cryst. Solids*, 271 [1–2] 94–99 (2000).
51. R. Müller, E. D. Zanotto, and V. M. Fokin, "Surface Crystallization of Silicate Glasses: Nucleation Sites and Kinetics," *J. Non-Cryst. Solids*, 274 [1–3] 208–231 (2000).
52. M. C. Weinberg, D. R. Uhlmann, and E. D. Zanotto, "Nose Method of Calculating Critical Cooling Rates for Glass-Formation," *J. Am. Ceram. Soc.*, 72 [11] 2054–2058 (1989).
53. M. C. Weinberg, B. J. Zelinski, D. R. Uhlmann, and E. D. Zanotto, "Critical Cooling Rate Calculations for Glass-Formation," *J. Non-Cryst. Solids*, 123 [1–3] 90–96 (1990).
54. E. D. Zanotto, "The Formation of Unusual Glasses by sol-gel Processing," *J. Non-Cryst. Solids*, 147 820–823 (1992).
55. A. A. Cabral, C. Fredericci, and E. D. Zanotto, "A Test of the Hruby Parameter to Estimate Glass-Forming Ability," *J. Non-Cryst. Solids*, 219 182–186 (1997).
56. A. A. Cabral, A. A. D. Cardoso, and E. D. Zanotto, "Glass-Forming Ability Versus Stability of Silicate Glasses. I. Experimental Test," *J. Non-Cryst. Solids*, 320 [1–3] 1–8 (2003).
57. L. M. Guimarães and E. D. Zanotto, "Crystallization and Critical Cooling Rate to Vitrify Poly(Decamethylene Sebacate)," *Quim. Nova*, 26 [2] 202–207 (2003) (in Portuguese).
58. M. L. F. Nascimento, L. A. Souza, E. B. Ferreira, and E. D. Zanotto, "Can Glass Stability Parameters Infer Glass Forming Ability?" *J. Non-Cryst. Solids*, 351 [40–42] 3296–3308 (2005).
59. L. Zhang, R. K. Brow, M. E. Schlesinger, L. Ghussn, and E. D. Zanotto, "Glass Formation From Iron-Rich Phosphate Melts," *J. Non-Cryst. Solids*, 356 [25–27] 1252–1257 (2010).
60. L. Zhang, L. Ghussn, M. L. Schmitt, E. D. Zanotto, R. K. Brow, and M. E. Schlesinger, "Thermal Stability of Glasses From the Fe₄(P₂O₇)₃-Fe(PO₃)₃ System," *J. Non-Cryst. Solids*, 356 [SI 52–54] 2965–2968 (2010).
61. E. B. Ferreira, *et al.*, "Critical Analysis of Glass Stability Parameters and Application to Lithium Borate Glasses," *J. Am. Ceram. Soc.*, 94 [11] 3833–3841 (2011).
62. M. O. Prado, E. D. Zanotto, and R. Müller, "Model for Sintering Polydispersed Glass Particles," *J. Non-Cryst. Solids*, 279 [2–3] 169–178 (2001).
63. E. D. Zanotto and M. O. Prado, "Isothermal Sintering With Concurrent Crystallisation of Monodispersed and Polydispersed Glass Particles. Part.I," *Phys. Chem. Glasses*, 42 [3] 191–198 (2001).
64. M. O. Prado and E. D. Zanotto, "Glass Sintering With Concurrent Crystallization," *C. R. Chim.*, 5 [11] 773–786 (2002).
65. M. O. Prado, C. Fredericci, and E. D. Zanotto, "Glass Sintering With Concurrent Crystallisation. Part.II. Nonisothermal Sintering of Jagged Polydispersed Particles," *Phys. Chem. Glasses*, 43 [5] 215–223 (2002).
66. M. O. Prado, E. D. Zanotto, and C. Fredericci, "Sintering Polydispersed Spherical Glass Particles," *J. Mater. Res.*, 18 [6] 1347–1354 (2003).
67. M. O. Prado, C. Fredericci, and E. D. Zanotto, "Isothermal Sintering With Concurrent Crystallization of Polydispersed Soda-Lime-Silica Glass Beads," *J. Non-Cryst. Solids*, 331 [1–3] 145–156 (2003).
68. M. O. Prado, C. Fredericci, and E. D. Zanotto, "Non-Isothermal Sintering With Concurrent Crystallization of Polydispersed Soda-Lime-Silica Glass Beads," *J. Non-Cryst. Solids*, 331 [1–3] 157–167 (2003).
69. M. O. Prado, E. B. Ferreira, and E. D. Zanotto, "Sintering Kinetics of Crystallizing Glass Particles – A Review," *Melt Chemistry, Relaxation, and Solidification Kinetics of Glasses*, American Ceramic Society, *Ceram. Trans.*, 170 163–179 (2005).
70. M. J. Pascual, A. Duran, M. O. Prado, and E. D. Zanotto, "Model for Sintering Devitrifying Glass Particles With Embedded Rigid Fibers," *J. Am. Ceram. Soc.*, 88 [6] 1427–1434 (2005).
71. M. O. Prado, M. L. F. Nascimento, and E. D. Zanotto, "On the Sinterability of Crystallizing Glass Powders," *J. Non-Cryst. Solids*, 354 [40–41] 4589–4597 (2008).
72. V. O. Soares, R. C. V. M. Reis, E. D. Zanotto, M. J. Pascual, and A. Durán, "Non-Isothermal Sinter-Crystallization of Jagged Li₂O–Al₂O₃–SiO₂ Glass and Simulation Using a Modified Form of the Clusters Model," *J. Non-Cryst. Solids*, 358 [23] 3234–3242 (2012).
73. R. M. C. V. Reis, "Assessment of viscous sintering models and determination of crystal growth rate and crystallized fraction in glasses," PhD Thesis in Materials Science and Engineering, Federal University of São Carlos, (2012) (in Portuguese).
74. N. D. Mora, E. D. Zanotto, and V. M. Fokin, "Crystal Growth and Viscous Flow in Cordierite and Other Glasses," *Phys. Chem. Glasses*, 39 [2] 91–97 (1998).
75. A. C. S. Sabioni, E. D. Zanotto, F. Millot, and H. L. Tuller, "Oxygen Self-Diffusion in a Cordierite Glass," *J. Non-Cryst. Solids*, 242 [2–3] 177–182 (1998).
76. M. L. F. Nascimento and E. D. Zanotto, "Diffusion Processes in Vitreous Silica Revisited," *Phys. Chem. Glasses: Eur. J. Glass Sci. Technol. B*, 48 [4] 201–217 (2007).
77. M. L. F. Nascimento and E. D. Zanotto, "Mechanisms and Dynamics of Crystal Growth, Viscous Flow, and Self-Diffusion in Silica Glass," *Phys. Rev. B*, 73 [2] 024209 (2006).
78. V. M. Fokin, J. W. P. Schmelzer, M. L. F. Nascimento, and E. D. Zanotto, "Diffusion Coefficients for Crystal Nucleation and Growth in Deeply

- Undercooled Glass-Forming Liquids," *J. Chem. Phys.*, 126 [23] 234507 (2007).
79. V. M. Fokin, O. V. Potapov, V. L. Ugolkov, E. D. Zanotto, and F. M. Spiandorello, "The Kinetics of Crystallization of Solid Solutions in a Glass of the Stoichiometric Composition $\text{Na}_2\text{O}\cdot 2\text{CaO}\cdot 3\text{SiO}_2$," *Russ. J. Phys. Chem.*, 77 [10] 1639–1641 (2003).
80. M. L. F. Nascimento, E. B. Ferreira, and E. D. Zanotto, "Kinetics and Mechanisms of Crystal Growth and Diffusion in a Glass-Forming Liquid," *J. Chem. Phys.*, 121 [18] 8924–8928 (2004).
81. V. M. Fokin, M. L. F. Nascimento, and E. D. Zanotto, "Correlation Between Maximum Crystal Growth Rate and Glass Transition Temperature of Silicate Glasses," *J. Non-Cryst. Solids*, 351 [10–11] 789–794 (2005).
82. V. M. Fokin, N. S. Yuritsyn, E. D. Zanotto, J. W. P. Schmelzer, and A. A. Cabral, "Nucleation Time-lag From Nucleation and Growth Experiments in Deeply Undercooled Glass-Forming Liquids," *J. Non-Cryst. Solids*, 354 [32] 3785–3792 (2008).
83. ??? ???? and ??? ???? , "???" ???, ??? ????-???? (????). **5**
84. M. L. F. Nascimento and E. D. Zanotto, "Does Viscosity Describe the Kinetic Barrier for Crystal Growth From the Liquidus to the Glass Transition?" *J. Chem. Phys.*, 133 [17] ???-???? (2010). **6**
85. M. L. F. Nascimento, V. M. Fokin, E. D. Zanotto, and A. S. Abyzov, "Dynamic Processes in a Silicate Liquid From Above Melting to Below the Glass Transition," *J. Chem. Phys.*, 135 [19] ???-???? (2011). **7**

UNCORRECTED PROOF

Author Query Form

Journal: IJAG
Article: 12022

Dear Author,

During the copy-editing of your paper, the following queries arose. Please respond to these by marking up your proofs with the necessary changes/additions. Please write your answers on the query sheet if there is insufficient space on the page proofs. Please write clearly and follow the conventions shown on the attached corrections sheet. If returning the proof by fax do not write too close to the paper's edge. Please remember that illegible mark-ups may delay publication.

Many thanks for your assistance.

Query reference	Query	Remarks
1	AUTHOR: A running head short title was not supplied; please check if this one is suitable and, if not, please supply a short title of up to 40 characters that can be used instead.	
2	AUTHOR: Please indicate if the author of this paper is an ACerS (American Ceramic Society) member."	
3	AUTHOR: Papers that are submitted but not yet accepted for publication should not be included in the reference list. They can be cited in the text by referring to them as 'unpublished data'. Therefore, either update the reference [1] giving the publication date (if now published) or changing to 'in press' (if now accepted for publication), or remove it from the reference list and change all citations in the text to 'unpublished data', and renumber rest of the references.	
4	AUTHOR: Please confirm that Journal title 'J. de Physique' has been abbreviated correctly.	
5	AUTHOR: Please provide the author name(s), author name(s), year of publication, journal title, article title, volume number, page range for reference [83].	
6	AUTHOR: Please provide the page range for reference [84].	
7	AUTHOR: Please provide the page range for reference [85].	

Proof Correction Marks

Please correct and return your proofs using the proof correction marks below. For a more detailed look at using these marks please reference the most recent edition of The Chicago Manual of Style and visit them on the Web at: <http://www.chicagomanualofstyle.org/home.html>

<i>Instruction to typesetter</i>	<i>Textual mark</i>	<i>Marginal mark</i>
Leave unchanged	... under matter to remain	<u>stet</u>
Insert in text the matter indicated in the margin	^	^ followed by new matter
Delete	Ʒ through single character, rule or underline or Ʒ through all characters to be deleted	Ʒ
Substitute character or substitute part of one or more word(s)	Ƶ through letter or —— through characters	new character Ƶ or new characters Ƶ
Change to italics	— under matter to be changed	<u>ital</u>
Change to capitals	≡≡ under matter to be changed	<u>Caps</u>
Change to small capitals	≡≡ under matter to be changed	<u>sc</u>
Change to bold type	~ under matter to be changed	<u>bf</u>
Change to bold italic	~ under matter to be changed	<u>bf+ital</u>
Change to lower case	Ɔ	<u>lc</u>
Insert superscript	∨	∨ under character e.g. ∨
Insert subscript	^	^ over character e.g. ^
Insert full stop	⊙	⊙
Insert comma	↕	↕
Insert single quotation marks	↙ ↘	↙ ↘
Insert double quotation marks	↗ ↖	↗ ↖
Insert hyphen	=	=
Start new paragraph	¶	¶
Transpose	┌┐	┌┐
Close up	linking ○ characters	○
Insert or substitute space between characters or words	#	#
Reduce space between characters or words	⌒	⌒